

## PATENT ABSTRACTS OF JAPAN

Ref.1

(11)Publication number : 03-210349

(43)Date of publication of application : 13.09.1991

(51)Int.Cl.

C08L 23/08

C08L 23/08

C09D123/08

(21)Application number : 02-005412

(71)Applicant : MITSUI PETROCHEM IND LTD

(22)Date of filing : 12.01.1990

(72)Inventor : TOKITA TAKU  
TAKADA YUKIHIRO  
INAGAKI HAJIME

## (54) AQUEOUS COPOLYMER DISPERSION, PREPARATION THEREOF, AND COATING FILM FORMED THEREFROM

## (57)Abstract:

PURPOSE: To improve the adhesiveness and film-forming properties by dispersing a partially neutralized ethylene-acrylic acid copolymer in an aq. dispersion of a partially neutralized ethylene-methacrylic acid copolymer.

CONSTITUTION: 80-20wt.% partially neutralized ethylene-acrylic acid copolymer having an acrylic acid content of 5-45wt.% and an MFR of 1-4500g/10min is dispersed in an aq. dispersion of 20-80wt.% partially neutralized ethylene-methacrylic acid copolymer having a methacrylic acid content of 5-45wt.% and MFR (190° C, ASTM D1238) of 0.1-30g/10min, to give a copolymer compsn. contg. 5-50wt.% the sum of the two copolymers and having a viscosity of 30-250cP. The resulting compsn. is applied to a substrate, heated and baked at 80-250° C for 20sec to 10min, giving a coating film with a thickness of 10µm or higher.